

PATTERSON RENTAL TOOLS

TUB278PH6S135



¹Rotating Operational Torque is provided to allow for additional rotating torque if needed based on well conditions. Operational torque is not to be applied with tongs at the rotary, but with rotating equipment used to rotate the tubing in the well. Maximum make up torque should be applied at the rotary with calibrated tubing tongs before operational torque is applied to the tubing. Breakout torque will be approximately 80% of the maximum operational torque applied to the tubing. Extra care will need to be taken during the breakout process to prevent damage to the tubing and tubing handling equipment. Operational Torque is based on 65% of the connection's torsion yield.

2 7/8" 7.9# S-135 PH-6 Hydril Type Tubing

Tube Size:	2 7/8	in
Nominal Weight / Ft.	7.9	lbs/ft
Tube Grade:	S-135	
Connection:	PH-6	
Hard Banding/Coating	NONE	
Stencil Markings:	"P"	
ID Markings:	2 GROOVES	
TUBULAR SPECIFICATIONS		
Tube OD:	2.875	in
Tube ID:	2.323	in
Grade:	S-135	
Wall:	0.276	in
Drift OD:	2.229	in
Yield in Tension:	304,000	lbs
Burst Pressure Yield:	22,680	psi
Collapse Pressure Yield:	33,430	psi
Tube Compression Yield:	304,000	lbs
Torsion Yield:	17,378	ft-lbs
Bending Yield:	215	° /100ft
CONNECTION SPECIFICATIONS		
Connection OD:	3.438	in
Connection ID:	2.265	in
Make-Up Loss:	3.312	in
Tension Efficiency:	108	%
Connection Burst Yield:	22,680	psi
Connection Collapse Yield:	23,430	psi
Connection Compression Yield:	348,597	lbs
Connection Torsion Yield:	13,313	ft-lbs
Connection Bend Yield	258	° /100ft
¹ Rotating Operational Torque:	8,653	ft-lbs
MAKE-UP TORQUE		
Minimum Make-Up Torque:	3,500	ft-lbs
Optimum Make-Up Torque:	3,938	ft-lbs
Maximum Make-Up Torque:	4,375	ft-lbs

* Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, Patterson Services, Inc. makes no representation about, and is not responsible or liable for the accuracy or reliability of the data, described herein. Nothing contained in this document shall be considered a recommendation for any use that may infringe patent rights, or an endorsement of any particular material, equipment, service, or other item. The properties listed in this document are not specification. They are provided as information only and in no way modify, amend, enlarge or create any specification or warranty.