## **Drill Pipe Data & Performance Sheet**

# 3-1/2" 15.50# X-95 R2 NC38 (3-1/2 IF)

#### **TUBE BODY DATA**

Tube OD	3.500	in.
Wall Thickness	0.449	in.
Tube ID	2.602	in.
Tensile Yield Strength	317,500	lbs. (API Premium 80% Inspection Class)
Torsional Yield Strength	20,500	ft-lbs. (API Premium 80% Inspection Class)
Upset Type   Upset OD (max)		EU 3.875 in.
Elevator Capacity	693,045	lbs.
Tube Burst	19,499	psi. (API Premium 80% Inspection Class)
Tube Collapse	18,331	psi. (API Premium 80% Inspection Class)
Slip-Crush Capacity (16.5" gripper contact length)	318,900	lbs.

#### CONNECTION DATA

Connection	NC38 (3-1/2 IF)		
<b>Tool Joint OD</b>	4.875 in.		
Tool Joint ID	2.563 in.		
Tool Joint SMYS	120,000 psi.		

#### **CONNECTION PERFORMANCE**

Make Up Torque (Max.) <sup>1</sup>	12,100 13,915	ft-lbs. (1.0 FF) ft-lbs. (1.15 FF)
Connection Tensile Yield (@ Max. M/U TQ)	538,600	lbs.
<b>Connection Torsional Yield</b>	20,100	ft-lbs.

## **ENGINEERING DATA**

Approximate Length	31	ft.		
Drift Diameter	2.438	in.		
Adj. Weight	16.72	lbs. / ft.		
Displacement	0.2554	gal. / ft.	0.0061	bbls. / ft.
Capacity	0.2754	gal. / ft.	0.0066	bbls. / ft.

## Notes:

¹Max MUT 1.0 FF is 60% of connection torsional strength. As required, adjust MUT according to applied thread compound friction factor, not exceeding 1.15. Rec MUT for most applications is that shown for 1.0 FF, regardless of dope used. Higher MUT should only be applied where rotary torque exceeds 80% of MUT 1.0 FF or when downhole torque and/or backoff is a concern.

The technical information contained herein, including the product performance sheet and other attached documents, has been extracted from information available from the manufacturer and is for reference only and not a recommendation. The user is fully responsible for the accuracy and suitability of use of the technical information. Patterson Servicers, Inc. cannot assume responsibility for the results obtained through the use of this material. No expressed or implied warranty is intended. Drill pipe assembly properties are calculated based on uniform OD and wall thickness. No safety factor is applied. Weight, displacement, and capacity are approximate and can vary by ± 10% (or more) depending on OD, specified wall, wall tolerance, and internal coating options. It is the responsibility of the customer and the end user to determine the appropriate performance ratings, acceptable use of the product, maintain safe operational practices, and to apply a prudent safety factor suitable for the application. For API connections that have different pin and box IDs, tool joint ID refers to the pin ID. Per Chapter B, Section 4 VII of the IADC drilling manual, it is recommended that drilling torque should not exceed 80% of MUT.







